



Technical Data Sheet

CrystalCoat™ UV MP-2600

Abrasion Resistant UV-Cure Coating

DESCRIPTION

CrystalCoat™ UV MP-2600 is a 1.49 refractive index abrasion resistant UV cured hard-coat. Thermal post-cure required to reach full abrasion resistance

FEATURES

- Abrasion Resistance
- Primer-Free Adhesion to Polycarbonate
- Strippable in Caustic Solution
- Compatible with Anti-reflective and Metalizing Treatments

STORAGE AND USE

Recommended storage temperature for UV MP-2600 is -18°C (0°F). When stored at this temperature it is recommended to use UV MP-2600 within three (3) months of the date received.

SOLUTION PROPERTIES

PROPERTY	TYPICAL VALUES
Solids	34.5 - 36.5 %
Viscosity @ 25°C	≤ 11.0 cP
Density @ 25°C	1.00 - 1.02 g/mL
Solvents: Water, Methanol, Ethanol, Isopropanol, PM Glycol Ether, EB Glycol Ether	

CURED COATING PROPERTIES

PROPERTY	TYPICAL VALUES
Coating Thickness	3.0 - 5.0 µm
Refractive Index	1.49
Adhesion	100 %
Bayer Ratio	≥ 2.0

RECOMMENDED OPERATING GUIDELINES

PROPERTY	TYPICAL VALUES
Environmental Conditions	20 - 25°C, 35 - 50% RH
Air Flow	Filtered, Laminar (Class 100)
Coating Temperature	18 - 23°C
Coating Filtration	5 - 10 µm absolute
Spin Speed	1300—1800 rpm
Air Dry Time	20 - 60 seconds
UV Cure (as measured by EIT UV Power Puck)	0.9 - 1.0 J/cm ²
Thermal Post Cure	128°C for 1hr



CrystalCoat™ UV MP-2600

Abrasion Resistant UV Cure Coating

SDC TECHNOLOGIES CONTACT INFORMATION

Corporate Headquarters - USA

45 Parker, Suite 100
Irvine, California 92618 USA
800-272-7681 (Toll-Free USA)
+1-714-939-8300
technicalsupport.ca@sdctech.com

Europe Office

Unit 6 John Baker Close
Llantarnam Industrial Park
Cwmbran, Torfaen
NP44 3AX, United Kingdom
+44-1633-627030
technicalsupport.eu@sdctech.com

China Office

No. 1585 Gumei Road
Xuhui District
Shanghai 200233
PR China
+86-21-61995035
customer-care.cn@sdctech.com

Singapore Office

27 Tuas South Street 1
Singapore 638035
+65-6210-6355
customer-care.ap@sdctech.com



sdctech.com

CrystalCoat™ is trademark of SDC Technologies.

Teflon® is a registered trademark of The Chemours Company FC, LLC.

©2018 SDC Technologies, Inc. All rights reserved. SDC Technologies is a wholly-owned subsidiary of Mitsui Chemicals, Inc.

EQUIPMENT PREPARATION

Equipment Cleaning: Coating equipment should be cleaned prior to use of UV MP-2600 in order to avoid any possible contamination problems. The cleaning process should include multiple solvent rinses (utilizing a solvent compatible with the material in prior use with the equipment) followed by a thorough PM Glycol Ether rinse. PM Glycol Ether should also be used for cleaning equipment after the use of UV MP-2600.

Equipment Materials: All equipment surfaces that are exposed to UV MP-2600 should be constructed of stainless steel, polypropylene or Teflon®. Other materials should be tested for compatibility with UV MP-2600 prior to use. Materials made with polyvinyl chloride (PVC) should not be used under any circumstances with UV MP-2600 or other primers or coatings that contain glycol ethers.

PRETREATMENT AND CLEANING OF SUBSTRATE

Prior to coating with UV MP-2600, parts should be clean and free of any surface residues. Polycarbonate parts that are injection molded should be cleaned with a neutral detergent solution to remove any residues left on the parts from the molding process, and then rinsed thoroughly with de-ionized water.

HEALTH & SAFETY INFORMATION

Before using this product, read and understand the Safety Data Sheet, SDS, which provides information on health, physical, and environmental hazards, handling precautions and first aid recommendations. For a copy of an SDS, contact a sales or customer service representative.

WARRANTY & LIABILITY LIMITATIONS

Information contained herein is accurate to the best of our knowledge. The coating solution properties and cured coating properties listed herein represent typical values for UV MP-2600 and are not meant as specifications. SDC Technologies, Inc. insists that users conduct their own tests for applicability and fitness for any purpose. Statements concerning use of products or formulations described herein shall not be construed as a warranty or license to infringe any patent or trademark, and no liability for infringement arising out of such use is assumed. Please refer to SDC Technologies' Standard Terms and Conditions or to your Purchase Agreement with SDC for the warranty coverage of SDC's product.

PRODUCT SHIPPING & AVAILABILITY

Typical lead-time for shipment of UV MP-2600 is four (4) weeks from confirmation of a purchase order. SDC provides several shipping options. Please contact an SDC representative to determine which option best fits your needs. All orders are shipped ex works/F.O.B. Additional shipment charges