

CrystalChrome® HC

Abrasion Resistant Coating

SOLUTION PROPERTIES

PROPERTY	TYPICAL VALUES
Solids	23 - 25 %
Viscosity @ 25°C	≤ 8.0 cP
Density @ 25°C	0.95 - 1.00 g/ml
Solvents: Water, Methanol, Ethanol, Isopropanol, PM Glycol Ether	

CURED COATING PROPERTIES

PROPERTY	TYPICAL VALUES
Coating Thickness	2.5 - 3.5 µm
Refractive Index	1.49
Bayer Ratio	3.0 - 3.5
Adhesion	100 %

RECOMMENDED OPERATING GUIDELINES

PROPERTY	TYPICAL VALUES
Environmental Conditions	20 - 25 °C, 25 - 40 % RH
Air Flow	Filtered, Laminar
Coating Temperature	16 - 18 °C
Coating Filtration	5 - 10 µm absolute
Extraction Speed	1.0 - 2.0 mm/s
Air Dry	<30 s
Dry Time/Temperature	10 mins @ 70 °C
Cure Conditions	4hrs @ 110 °C

DESCRIPTION

CrystalChrome® HC is a polysiloxane based thermal cure hard coat designed for use with SDC's CrystalChrome Photochromic coating system.

FEATURES

- Abrasion Resistance
- Chemical Resistance
- Optical Clarity
- Compatible with Anti-reflective and metalizing treatments

STORAGE AND USE

The recommended storage temperature for CrystalChrome HC is 4°C (40°F).

When stored at this temperature in the original closed container, it is recommended to start use of CrystalChrome HC within 3 months of the date received.

For extended periods (3-6 months) of storage CrystalChrome HC should be stored at -18°C (0°F).



CrystalChrome® HC

Abrasion Resistant Coating

SDC TECHNOLOGIES CONTACT INFORMATION

Corporate Headquarters - USA
45 Parker, Suite 100
Irvine, California 92618 USA
800-272-7681 (Toll-Free USA)
+1-714-939-8300
technicalsupport.ca@sdctech.com

Europe Office
Unit 7, Avondale Industrial Estate
Pontrhydryn, Cwmbran
NP44 1UG, Great Britain
+44-1633-627030
technicalsupport.eu@sdctech.com

China Office
No. 1585 Gumei Road
Xuhui District
Shanghai 200233
China
+86-21-61517768
customer-care.cn@sdctech.com

Singapore Office
27 Tuas South Street 1
Singapore 638035
+65-6210-6355
customer-care.ap@sdctech.com



sdctech.com

CrystalChrome® is a registered trademark of SDC Technologies.

Teflon® is a registered trademark of The Chemours Company FC, LLC.

©2023 SDC Technologies, Inc. All rights reserved. SDC Technologies is a wholly-owned subsidiary of Mitsui Chemicals, Inc

20190315_CCHC

EQUIPMENT PREPARATION

Equipment Cleaning: Coating equipment should be cleaned prior to use of CrystalChrome HC in order to avoid any possible contamination problems. Coating contamination can result in adhesion problems or general appearance problems. The cleaning process should include multiple solvent rinses (utilizing a solvent compatible with the material in prior use with the equipment) followed by a thorough PM Glycol Ether rinse. PM Glycol Ether should also be used for cleaning equipment after the use of CrystalChrome HC.

Equipment Materials: All equipment surfaces that are exposed to CrystalChrome HC should be constructed of stainless steel, polyethylene, polypropylene or Teflon®. Other materials should be tested for compatibility with CrystalChrome HC prior to use. Materials made with polyvinyl chloride (PVC) should not be used under any circumstances with HC or other primers or coatings that contain glycol ethers.

PRETREATMENT AND CLEANING OF SUBSTRATE

CrystalChrome HC is designed for use with CrystalChrome Photochromic coating system. Refer to the relevant CrystalChrome TDS's for recommended substrate preparation prior to coating with CrystalChrome HC.

SOLUTION MANAGEMENT

For optimum performance, CrystalChrome HC should be maintained in a % solids range of 23 - 25 %. Higher or lower solids can cause appearance problems or lead to a coating deposition that is either too thick or too thin, respectively. The % solids should be measured on a regular basis and adjusted as needed by the addition of SM-835A a 90/10 mixture of denatured ethanol and PM glycol ether. Denatured ethanol formulations that contain methanol, isopropanol and <1% water can be used.

HEALTH AND SAFETY INFORMATION

Before using this product, read and understand the Safety Data Sheet, SDS, which provides information on health, physical, and environmental hazards, handling precautions and first aid recommendations. For a copy of an SDS, contact a sales or customer service representative.

WARRANTY AND LIABILITY LIMITATIONS

Information contained herein is accurate to the best of our knowledge. The coating solution properties and cured coating properties listed herein represent typical values for CrystalChrome HC and are not meant as specifications. SDC Technologies, Inc. insists that users conduct their own tests for applicability and fitness for any purpose. Statements concerning use of products or formulations described herein shall not be construed as a warranty or license to infringe any patent or trademark, and no liability for infringement arising out of such use is assumed. Please refer to SDC Technologies' Standard Terms and Conditions or to your Purchase Agreement with SDC for the warranty coverage of SDC's product.

PRODUCT SHIPPING AND AVAILABILITY

Typical lead-time for shipment of CrystalChrome HC is four (4) weeks from confirmation of a purchase order. SDC provides several shipping options. Please contact an SDC representative to determine which option best fits your needs.