



Technical Data Sheet

CrystalCoat® UV P-201B

UV-Cure Spin Coat Primer

DESCRIPTION

CrystalCoat® UV P-201B is a UV curable primer for ophthalmic lenses or other plastic parts. Designed to provide an adhesion layer for application to CR-39® and Mid-index substrates.

FEATURES

- Solvent-Based Formulation
- Designed for ADC (CR-39®, RAV 7™), Trivex®, Mid-Index Acrylic
- Spin, Flow, or Spray Application

STORAGE AND USE

UV P-201B is flammable and should be stored away from potential ignition sources. Store UV P-201B in closed, properly label containers. Do not store in colorless glass containers or other containers that transmit UV light. Do not pad containers or pressurized vessels using nitrogen. Use of nitrogen may cause premature gelling. Avoid sunlight and other sources of UV Light. Store at ambient temperatures less than 75°F/24°C.

SOLUTION PROPERTIES

PROPERTY	TYPICAL VALUES
% Solids	3%
Viscosity @ 25°C	1.2 - 1.3 cP

CURED COATING PROPERTIES

PROPERTY	TYPICAL VALUES
Coating Thickness	.03 – .06 µm
Adhesion (30 Min. Boiling Water)	100 %

RECOMMENDED OPERATING GUIDELINES

PROCESS	TYPICAL VALUES
Wash	Wash in soap and water. No etching required.
Application Spin Speed*	600 rpm for 5 seconds
Spin Out Speed	1800 rpm for 20 seconds
Cure	10-15 feet per minute with Fusion F300 H+bulb (0.30-0.40 joules/cm ²)

*Spin speeds and times can vary depending on equipment utilized. These parameters are meant as a guideline. UV P-201B can also be applied by spray or flow coating.



CrystalCoat® UV P-201B

UV-Cure Spin Coat Primer

CONTACT INFORMATION

**SDC Technologies—Americas
Corporate Headquarters—N.A.**
45 Parker, Suite 100
Irvine, California 92618 USA
800-272-7681 (Toll-Free USA)
+1-714-939-8300
technicalsupport.ca@sdctech.com

Europe Office
Unit 7, Avondale Industrial Estate
Pontrhydryn, Cwmbran
NP44 1UG, Great Britain
+44-1633-627030
Technicalsupport.eu@sdctech.com

China Office
No. 1585 Gumei Road
Xuhui District
Shanghai 200233
PR China
+86-21-61517768
customercare.cn@sdctech.com

Singapore Office
27 Tuas South Street 1
Singapore 638035
+65-6210-6355
customercare.ap@sdctech.com



sdctech.com

CrystalCoat® is a registered trademark of SDC Technologies, Inc.

CR-39® and Trivex® are registered trademarks of PPG.

MR-Series: MR-8™, MR-7™, MR-10™ & MR-174™ and RAV 7™ are trademarks of Mitsui Chemicals, Inc.

Teflon® is a registered trademark of The Chemours Company FC, LLC.

20240125

EQUIPMENT PREPARATION

Equipment Cleaning: Coating equipment should be cleaned prior to use of UV P-201B in order to avoid any possible contamination problems. The cleaning process should include multiple solvent rinses (utilizing a solvent compatible with the material in prior use with the equipment) followed by a thorough rinse with acetone or 1-Methoxy-2-propanol (PM). Acetone or PM should also be used for cleaning equipment after the use of UV P-201B. It is important to be sure all solvent has been completely removed/dried from coating bowl, tubing, and pump before adding primer.

Equipment Materials: All equipment surfaces that are exposed to UV P-201B should be constructed of stainless steel, polypropylene or Teflon®. Other materials should be tested for compatibility with UV P-201B prior to use. Materials made with polyvinyl chloride (PVC) should not be used under any circumstances.

APPLICATION ENVIRONMENT

UV P-201B should be applied in a clean temperature and humidity controlled environment. Recommended conditions for application are 20 – 25°C (68 - 77°F) and 30 – 60% relative humidity. Coating machine should be equipped with hepa air filter. It is recommended to place coating machine in a clean environment and in a separate area from potential contamination sources.

PARTS CLEANING

Parts to be primed with UV P-201B should first be cleaned isopropanol, then cleaned by inline cleaning system in the coating machine being used. Parts should be clean and dry before application of UV P-201B.

HEALTH & SAFETY INFORMATION

Before using this product, read and understand the Safety Data Sheet, SDS, which provides information on health, physical, and environmental hazards, handling precautions and first aid recommendations. For a copy of an SDS, contact a sales or customer service representative.

WARRANTY & LIABILITY LIMITATIONS

Information contained herein is accurate to the best of our knowledge. The primer solution properties and cured coating properties listed herein represent typical values for UV P-201B and are not meant as specifications. SDC Technologies, Inc. insists that users conduct their own tests for applicability and fitness for any purpose. Statements concerning use of products or formulations described herein shall not be construed as a warranty or license to infringe any patent or trademark, and no liability for infringement arising out of such use is assumed. Please refer to SDC Technologies Standard Terms and Conditions or to your Purchase Agreement with SDC for the warranty coverage of SDC's product.

PRODUCT SHIPPING & AVAILABILITY

Typical lead-time for shipment of UV P-201B is four (4) weeks from confirmation of a purchase order. SDC provides several shipping options. Please contact an SDC representative to determine which option best fits your needs.

©2024 SDC Technologies, Inc. All rights reserved. SDC Technologies is a wholly-owned subsidiary of Mitsui Chemicals, Inc.