

CrystalChrome® GY

Photochromic Dip Coating - Gray (all versions)

SOLUTION PROPERTIES

PROPERTY	TYPICAL VALUES
Solids	19 - 22 %
Viscosity @ 25°C	<40 cP
Solvents: PM Glycol Ether	

CURED COATING PROPERTIES

PROPERTY	TYPICAL VALUES
Coating Thickness	5.5 - 6.5 µm
Refractive Index	1.50
Adhesion	100 %

RECOMMENDED OPERATING GUIDELINES

PROPERTY	TYPICAL VALUES
Environmental Conditions	20 - 25 °C, 25 - 40 % RH
Air Flow	Filtered, Laminar (Class 100)
Coating Temperature	18 - 20 °C
Coating Filtration	5 µm absolute
Extraction Speed	2.0 - 3.0 mm/s
Air Dry	<30 s
Dry Time/Temperature	10 - 20 min @ 70 °C

DESCRIPTION

CrystalChrome® GY is a solvent based photochromic coating designed for dip coat applications to impart photochromic activity when activated with sunlight.

This TDS covers all current CrystalChrome GY (gray) products.

FEATURES

- Photochromic Gray
- Designed for dip coat application

STORAGE AND USE

The recommended storage temperature for CrystalChrome GY is 20 - 25 °C (68 - 77 °F).

When stored at this temperature in the original closed container, it is recommended to start use of CrystalChrome GY within 6 months of the date received.



CrystalChrome® GY

Photochromic Dip Coating - Gray

SDC TECHNOLOGIES CONTACT INFORMATION

Corporate Headquarters - USA
45 Parker, Suite 100
Irvine, California 92618 USA
800-272-7681 (Toll-Free USA)
+1-714-939-8300
technicalsupport.ca@sdctech.com

Europe Office
Unit 7, Avondale Industrial Estate
Pontrhydyrun, Cwmbran
NP44 1UG, Great Britain
+44-1633-627030
technicalsupport.eu@sdctech.com

China Office
No. 1585 Gumei Road
Xuhui District
Shanghai 200233
China
+86-21-61517768
customer-care.cn@sdctech.com

Singapore Office
27 Tuas South Street 1
Singapore 638035
+65-6210-6355
customer-care.ap@sdctech.com



sdctech.com

CrystalChrome® is a registered trademark of SDC Technologies.

Teflon® is a registered trademark of The Chemours Company FC, LLC.

©2024 SDC Technologies, Inc. All rights reserved. SDC Technologies is a wholly-owned subsidiary of Mitsui Chemicals, Inc.

20190315_CCGY

EQUIPMENT PREPARATION

Equipment Cleaning: Coating equipment should be cleaned prior to use of CrystalChrome GY in order to avoid any possible contamination problems. The cleaning process should include multiple solvent rinses (utilizing a solvent compatible with the material in prior use with the equipment) followed by a thorough PM Glycol Ether rinse. PM Glycol Ether should also be used for cleaning equipment after the use of CrystalChrome GY.

Equipment Materials: All equipment surfaces that are exposed to CrystalChrome GY should be constructed of stainless steel, polyethylene, polypropylene or Teflon®. Other materials should be tested for compatibility with CrystalChrome GY prior to use. Materials made with polyvinyl chloride (PVC) should not be used under any circumstances with CrystalChrome GY or other coatings that contain glycol ethers.

SAMPLE PREPARATION

Prior to coating with CrystalChrome GY parts should be clean and free of any surface residues. A typical process would be to clean in a 10% aqueous solution of sodium hydroxide at 60°C for 5 - 10 minutes. This cleaning should be followed by city water rinsing, then DI water rinsing and drying. Lenses should be completely clean, dry, and cooled before application of any coating or primer.

CrystalChrome GY can also be used in conjunction with either CrystalChrome® PR or CrystalChrome® ST. For details on how to prepare samples for use with these materials refer to their respective TDS's.

SOLUTION MANAGEMENT

For optimum performance, CrystalChrome GY coating solution should be maintained in a % solids range of 19 - 22 %. Higher or lower solids can cause appearance problems or lead to a coating deposition that is either too thick or too thin respectively. The % solids should be measured on a regular basis and adjusted as needed by the addition of PM Glycol Ether.

HEALTH AND SAFETY INFORMATION

Before using this product, read and understand the Safety Data Sheet, SDS, which provides information on health, physical, and environmental hazards, handling precautions and first aid recommendations. For a copy of an SDS, contact a sales or customer service representative.

WARRANTY AND LIABILITY LIMITATIONS

Information contained herein is accurate to the best of our knowledge. The coating solution properties and cured coating properties listed herein represent typical values for CrystalChrome GY and are not meant as specifications. SDC Technologies, Inc. insists that users conduct their own tests for applicability and fitness for any purpose. Statements concerning use of products or formulations described herein shall not be construed as a warranty or license to infringe any patent or trademark, and no liability for infringement arising out of such use is assumed. Please refer to SDC Technologies' Standard Terms and Conditions or to your Purchase Agreement with SDC for the warranty coverage of SDC's product.

PRODUCT SHIPPING AND AVAILABILITY

Typical lead-time for shipment of CrystalChrome GY is four (4) weeks from confirmation of a purchase order. SDC provides several shipping options. Please contact an SDC representative to determine which option best fits your needs.

ISO 9001:2015 and ISO 14001:2015 Certified