



Technical Data Sheet

CrystalCoat® PR-855

1.54 Refractive Index Primer

DESCRIPTION

CrystalCoat® PR-855 is a 1.54 refractive index solvent based primer designed to impart adhesion to COC substrate.

FEATURES

- Impact resistance
- Refractive Index 1.54
- Adhesion promoter on COC /APEL™ substrates
- Fast drying
- Optical clarity

STORAGE AND USE

The recommended storage temperature for PR-855 is -18°C (0°F). When stored at this temperature in the original closed container, it is recommended to start use of PR-855 within 6 months of the date received.

SOLUTION PROPERTIES

PROPERTY	TYPICAL VALUES
Solids	3.0 - 5.0 %
Viscosity @ 25°C	≤ 5 cP
Density	0.880 - 0.950 g/ml
Solvents: Water, Methanol, DAA	

CURED COATING PROPERTIES

PROPERTY	TYPICAL VALUES
Coating Thickness	0.2 - 0.6 µm
Refractive Index	1.54
Adhesion*	100 %

RECOMMENDED OPERATING GUIDELINES

PROPERTY	TYPICAL VALUES
Environmental Conditions	20 - 25°C, 20 - 60 % RH
Air Flow	Filtered, Laminar (Class 100)
Coating Temperature	8 - 18°C
Coating Filtration	1 - 5 µm absolute
Extraction Speed	1.0 - 2.0 mm/s
Dry Time/Temperature	5 min infrared heater or 10 min @ 70°C

* In order to achieve good adhesion on COC/COP substrates plasma treatment prior to application of the primer is recommended. See page 2 for suggested plasma treatment conditions.



CrystalCoat® PR-855

1.54 Refractive Index Primer

SDC TECHNOLOGIES CONTACT INFORMATION

Corporate Headquarters - USA
45 Parker, Suite 100
Irvine, California 92618 USA
800-272-7681 (Toll-Free USA)
+1-714-939-8300
technicalsupport.ca@sdctech.com

Europe Office
Unit 7, Avondale Industrial Estate
Pontrhydryn, Cwmbran
NP44 1UG, Great Britain
+44-1633-627030
technicalsupport.eu@sdctech.com

China Office
No. 1585 Gumei Road
Xuhui District
Shanghai 200233
China
+86-21-61517768
customercare.cn@sdctech.com

Singapore Office
27 Tuas South Street 1
Singapore 638035
+65-6210-6355
customercare.ap@sdctech.com



sdctech.com

CrystalCoat® is a registered trademark of SDC Technologies.

CR-39® is a registered trademark of PPG.

MR-8™, MR-7™, MR-10™, MR-174™ and APEL™ are registered trademarks of Mitsui Chemicals, Inc.

Teflon® is a registered trademark of The Chemours Company FC, LLC.

202292_PR-855

EQUIPMENT PREPARATION

Equipment Cleaning: Coating equipment should be cleaned prior to use of PR-855 in order to avoid any possible contamination problems. The cleaning process should include multiple solvent rinses (utilizing a solvent compatible with the material in prior use with the equipment) followed by a thorough methanol rinse. Methanol should also be used for cleaning equipment after the use of PR-855.

Equipment Materials: All equipment surfaces that are exposed to PR-855 should be constructed of stainless steel, polypropylene or Teflon®. Other materials should be tested for compatibility with PR-855 prior to use. Materials made with polyvinyl chloride (PVC) should not be used under any circumstances with PR-855 or other primers or coatings that contain glycol ethers.

PRETREATMENT AND CLEANING OF SUBSTRATE

Prior to coating with PR-855, parts should be clean and free of any surface residues.

Plasma Treatment (suggested conditions)

- * Base Pressure: 5.00 e⁻² Torr
- * Gas: Oxygen and Argon at 100 sccm
- * Gas Time: 30 sec
- * Power: 100 W
- * Generation Time: 5 min
- * Generation Frequency: 100 kHz

For information regarding application of PR-855 to other substrates, please contact SDC.

SOLUTION MANAGEMENT

For optimum performance, PR-855 coating solution should be maintained in a % solids range of 3.0 - 5.0 %. Higher or lower solids can cause appearance problems or lead to a coating deposition that is either too thick or too thin, respectively. The % solids should be measured on a regular basis and adjusted as needed by the addition of methanol (SM-700).

HEALTH AND SAFETY INFORMATION

Before using this product, read and understand the Safety Data Sheet, SDS, which provides information on health, physical, and environmental hazards, handling precautions and first aid recommendations. For a copy of an SDS, contact a sales or customer service representative.

WARRANTY AND LIABILITY LIMITATIONS

Information contained herein is accurate to the best of our knowledge. The coating solution properties and cured coating properties listed herein represent typical values for PR-855 and are not meant as specifications. SDC Technologies, Inc. insists that users conduct their own tests for applicability and fitness for any purpose. Statements concerning use of products or formulations described herein shall not be construed as a warranty or license to infringe any patent or trademark, and no liability for infringement arising out of such use is assumed. Please refer to SDC Technologies' Standard Terms and Conditions or to your Purchase Agreement with SDC for the warranty coverage of SDC's product.

PRODUCT SHIPPING AND AVAILABILITY

Typical lead-time for shipment of PR-855 is four (4) weeks from confirmation of a purchase order. SDC provides several shipping options. Please contact an SDC representative to determine which option best fits your needs.

ISO 9001:2015 and ISO 14001:2015 Certified

©2024 SDC Technologies, Inc. All rights reserved. SDC Technologies is a wholly-owned subsidiary of Mitsui

